



## PATENT ABSTRACTS OF JAPAN

(11) Publication number: 61000215 A  
(43) Date of publication of application: 06.01.1986

(51) Int. Cl. C08G 18/36  
C08G 18/66

(21) Application number: 59119882  
(22) Date of filing: 13.05.1984

(71) Applicant: DAINIPPON INK & CHEM INC  
(72) Inventor: SASAKI TAKAHITO  
UENO YUTAKA  
TSUNEKAWA YASUJI

(54) PRODUCTION OF OPEN-CELLULAR RIGID  
URETHANE FOAM

(57) Abstract:

PURPOSE: To obtain the titled urethane foam low in hygroscopicity and water absorptivity and excellent in heat resistance and low-temperature resistance, by using a polyol containing a specified ester of a higher fatty acid with a polyalcohol and a polyisocyanate as principal materials.

CONSTITUTION: In the production of an open-cellular

urethane foam by using a polyol and a polyisocyanate as principal materials, said polyol component contains at least 5wt%, based on the total polyol component, ester having at least one OH group, prepared by reacting a polyalcohol with an 8C or higher (un)saturated fatty acid (a product obtained by esterification of glycerin and soybean oil). It is possible to obtain an open-cellular rigid urethane foam low in hygroscopicity and water absorptivity and excellent in heat resistance and low-temperature resistance.

COPYRIGHT: (C)1986, JPO&Japio